RDC-156

VIBRATORY BALL MILL FOR GRAIN STABILITY

Technical information

Material type

FLECTRODES

LINING

RED IN-PLANT

When raw materials with coarse grains and low mechanical stability are used, breakage can occur during the green electrode preparation. When this happens, the surface area of the broken grains is not entirely covered by the binder. This can lead to crack formation during baking, graphitization, or during the utilization of the electrodes. In addition, low grain stability may also result in a grain size distribution finer than expected. For this purpose, it is important to ensure good grain stability of the different raw materials.

The measurement is conducted with the RDC-156 apparatus, where grains of the coarse fraction 8-4 mm are placed in a vibratory mill with steel balls for a given period of time. After the test, the grain stability is calculated and reported in %, as the ratio of grains still coarser than 4 mm to the initial sample weight.

Standard Method: ISO 10142 Property: Grain Stability [%] Sample: 100 g of granular carbon (natural 8-4 mm) **Process Time:** ~ 5 minutes Installation: Workbench Dimensions (LxWxH): 58 x 56 x 40 cm Weight: 90 kg **Electrical Property:** 400 V 3/N/PE, 50 Hz 0.2 kW, 0.5 A Certified Reference Material: **RDC 1156** Database Connection: No

Additional Recommended Equipment:

Drying oven (min. temperature 110°C) Weighing scale with an accuracy of 0.1 g Sieving machine (8 and 4 mm sieves)

RDC 1156



Weight per unit:

Number of tests:



600 g

6