

RDC-165

Name SÖDERBERG BAKING FURNACE BF12

Material type
**GRANULAR
PITCH
ELECTRODES
LINING**

Utilization
**R&D
IN-PLANT
LAB**

General description
For the quality control of Söderberg paste used in the aluminium or arc furnaces industries, some properties can be measured on the green paste itself, while others require the production of baked pilot electrodes.

These Söderberg pilot electrodes can be baked with the RDC-165 apparatus, in which a metallic bucket is placed that contains the green Söderberg paste. The temperature is increased according to a specific heat-up schedule. A given pressure is applied to the paste to ensure a density level like the real production conditions, the sample is protected with packing material to avoid any air oxidation during the heat treatment. The equipment is supplied with a tar incinerator unit for fume treatment purposes.

After baking, the metallic bucket that holds the baked pilot electrode can be removed and up to five core samples with 50 mm diameter can be drilled for analysis purposes by using the RDC-179 Pilot Core Drilling Machine.

Technical information	Function:	Baking of Söderberg paste
	Maximum Temperature:	1100° C
	Sample:	Söderberg paste
	Process Time:	~ 60 hours
	Installation:	Floor standing under fume hood
	Dimensions (LxWxH):	130 x 80 x 196 cm
	Weight:	380 kg
	Electrical Property:	400V 3/N/PE, 50 Hz 8 kW, 20 A
	Fluid Property:	Air, 5-7 bar
	Database Connection:	No

Additional Recommended Equipment:
Pilot Core Drilling Machine (RDC-179)
Test equipment for analysis
Weighing scale with an accuracy of 1 g
Oven (min. temperature 200 °C)

